## FRONT GLASS FOR ILLUMINATION

Publication number:

JP2002173338

**Publication date:** 

2002-06-21

Inventor:

YAMAMOTO HIROSHI; TODA TAKAHARU

Applicant:

**ASAHI TECHNO GLASS CORP** 

Classification:

- international:

C03C10/00; C03C10/00; (IPC1-7): C03C10/14

- european:

C03C10/00E2

Application number:

JP20000366506 20001201


Priority number(s):

JP20000366506 20001201

Report a data error here

## Abstract of **JP2002173338**

PROBLEM TO BE SOLVED: To provide front glass for illumination which is used for an illuminator and has excellent thermal impact resistance to prevent damage of a light source and splashing of glass splinters to the outside of lighting fixtures in case of the failure of the light source and to facilitate forming of the front glass for illumination. SOLUTION: This front lens for illumination is transparent crystallized glass which contains, by mass per cent, 58 to 70% SiO2, 18 to 25% Al2O3, 0.5 to 5% Li2O, 0 to 2% Na2O, 0 to 2% K2O, 1 to 5% MgO, 0 to 0.3% CaO, 0.1 to 2% BaO, 0.1 to 7% ZnO, 0.1 to 7% TiO2, 0.5 to 7% ZrO2 and 0.1 to 2.5% Sb2O3 and in which a &beta -quartz solid solution is deposited as a main crystal.



Data supplied from the esp@cenet database - Worldwide